

CLAIMS

1. (Previously presented) An aqueous acidic iron phosphorus bath comprising:
(A) at least one compound from which iron can be electrolytically deposited,
(B) hypophosphite ion, and
(C) a sulfur-containing compound comprising sulfoalkylated polyethylene imines, sulfonated safranin dye, and mercapto aliphatic sulfonic acids or alkali metal salts thereof.
2. (Original) The bath of claim 1 wherein the iron compound is selected from ferrous chloride, ferrous sulfate, ferrous fluoroborate, ferrous methane sulfonate, ferrous sulfamate and mixtures thereof.
3. (Previously presented) The bath of claim 1 wherein the hypophosphite ion is provided as hypophosphorus acid, an alkali metal hypophosphite salt, or a mixture thereof.
4. (Original) The bath of claim 1 wherein the sulfur-containing compound is a mercapto aliphatic sulfonic acid, an alkali metal salt thereof, or a mixture thereof.
5. (Cancelled)
6. (Previously presented) The electroplating bath of claim 1 further comprising aluminum ions.
7. (Original) The bath of claim 1 wherein the pH is from about 0.5 to about 5.

8. (Original) The bath of claim 1 wherein the bath is free of complexing agents.
9. (Previously presented) The bath of claim 1 wherein the iron compound comprises ferrous sulfate and ferrous chloride.
10. (Previously presented) An aqueous acidic iron phosphorus electroplating bath comprising:
 - (A) from about 20 to about 120 grams per liter of ferrous ion,
 - (B) from about 0.2 to about 8 grams per liter of phosphorus, said phosphorus being supplied as hypophosphite ion, and
 - (C) from about 0.001 to about 0.5 grams per liter of sulfur present as a sulfur-containing compound comprising sulfoalkylated polyethylene imines, sulfonated safranin dye, and mercapto aliphatic sulfonic acids or alkali metal salts thereof.
11. (Original) The electroplating bath of claim 10 wherein the ferrous ion is present as at least one salt selected from ferrous chloride, ferrous sulfate, ferrous fluoroborate, ferrous methane sulfonate, ferrous sulfamate, and mixtures thereof.
12. (Previously presented) The electroplating bath of claim 10 wherein the hypophosphite ion is from hypophosphorus acid, an alkali metal hypophosphite salt, or mixtures thereof.
13. (Original) The electroplating bath of claim 10 wherein the sulfur-containing compound is a mercapto aliphatic sulfonic acid compound or salt thereof.
14. (Cancelled)

15. (Previously presented) The electroplating bath of claim 10 wherein the bath further comprises from about 0.1 to about 10 grams per liter of aluminum ions.

16. (Original) The plating bath of claim 10 wherein the bath has a pH of from about 0.8 to about 2.5.

17. (Original) The plating bath of claim 10 wherein the bath is free of complexing agents.

18. (Previously presented) A process for electrodepositing an iron-phosphorus alloy on a conductive substrate which comprises:

- (A) providing the aqueous acidic iron phosphorus bath of claim 1, and
- (B) effecting the electrodeposition of the alloy on the substrate through the use of said bath.

19. (Original) The process of claim 18 wherein the substrate is a cylinder of an internal combustion engine.

20. (Previously presented) A process for electrodepositing an iron-phosphorus alloy on a conductive substrate which comprises:

- (A) providing the aqueous acidic iron phosphorus electroplating bath of claim 10, and
- (B) effecting the electrodeposition of the alloy on the substrate through the use of said bath.

21-24. (Cancelled)